

Vulcanized Compounds based on **SEPTON™ BIO-series** for Shoe Sole

- Vulcanized and PO crosslinking -

Elastomer R&D department
Elastomer division

kuraray **Septon™ BIO-series**

Excellent grip performance

Sample is showing the wet grip function

Golf grip



Grip tape
(Tennis etc.)



Shoe sole



Molding

Injection

Calender
Extrusion

Compression

V or Non-V

Non-V

Non-V

V

Formulation and properties for shoe sole (Target: Hs=60A±5)

Sample Name	Target	V-16	V-22	SBR	BIIR
SEPTON™ BIO-series	SF904	100	100		
E-SBR	JSR1502			100	
BIIR	BROMO BUTYL 2244				100
Sulfur ¹⁾	OT-20	2.25			
Sulfur ²⁾				1.8	1.8
Peroxide	Perhexa25B-40		4		
ZnO		3		3	3
Stearic acid		1		1	1
Vulcanization accelerator	DM	1.1		1.1	1.1
	TT	1.1		1.1	1.1
Silica	7000GR	10	10	25	25
Silane coupling	Si-69			1.5	1.5
Polyethylene glycol	PEG4000			1.5	1.5
EVA	EVA 560 (Tm= 90 deg. C)	15	15		
Tc(90)	160 deg. C	min	-	5.4	17
	180 deg. C	min	3.2	7.5	-
Coefficient of static friction	Dry	>5	6.4	7.1	3.1
	Wet	>2.5	3.9	2.8	1.4
Specific gravity		<1	0.96	0.94	1.09
Hardness	Type A	60±5	58	57	59
Tensile strength	MPa	>12	16	16	8.9
Elongation	%	>700	830	710	220
Tear strength	kN/m	>30	33	33	33
DIN abrasion	Mm ³	<200	202	279	146
					846

Molding conditions

(1)Tensile test piece (0.5 mm)
: Tc(90) x 1.2

(2)DIN test piece (8 mm)
: Tc(90) x 1.5

V-16: (1)180 deg. C, 3.8 min.
(2)180 deg. C, 4.8 min.

V-22: (1)180 deg. C, 9.0 min.
(2)180 deg. C, 11.3 min.

SBR: (1)160 deg. C, 6.5 min.
(2)160 deg. C, 8.1 min.

BIIR: (1)160 deg. C, 20.4 min.
(2)160 deg. C, 25.5 min.

Formulation and properties for shoe sole (Target: Hs=65A±5)

Sample Name	Target	V-26	V-41	SBR	BIIR
SEPTON™ BIO-series	SF904	100	100		
E-SBR	JSR1502			100	
BIIR	BROMO BUTYL 2244				100
Sulfur ¹⁾	OT-20	2.25			
Sulfur ²⁾				1.8	1.8
Peroxide	Perhexa25B-40		4		
ZnO		3		3	3
Stearic acid		1		1	1
Vulcanization accelerator	DM	1.1		1.1	1.1
	TT	1.1		1.1	1.1
Silica	7000GR	10	10	25	25
Silane coupling	Si-69			1.5	1.5
Polyethylene glycol	PEG4000			1.5	1.5
EVA	VA=14wt% (Tm= 90 deg. C)	25	25		
Bio-LDPE			10		
Tc(90)	160 deg. C	min	9.5	-	5.4
	180 deg. C	min	-	6.8	-
Coefficient of static friction	Dry	>5	6.9	5.8	3.1
	Wet	>2.5	2.6	2.1	1.4
Specific gravity		<1	0.97	0.94	1.09
Hardness	Type A	65±5	61	61	59
Tensile strength	Mpa	>12	18	12	8.9
Elongation	%	>700	770	560	220
Tear strength	kN/m	>30	50	48	33
DIN abrasion	mm ³	<200	138	209	146
					846

Molding conditions

(1)Tensile test piece (0.5 mm)
: Tc(90) x 1.2
(2)DIN test piece (8 mm)
: Tc(90) x 1.5

V-26: (1)160 deg. C, 11 min.
(2)160 deg. C, 14 min.

V-41: (1)180 deg. C, 8.2 min.
(2)180 deg. C, 10 min.

SBR: (1)160 deg. C, 6.5 min.
(2)160 deg. C, 8.1 min.

BIIR: (1)160 deg. C, 20.4 min.
(2)160 deg. C, 25.5 min.

Materials

SEPTON™ BIO-series SF904 (Kuraray Co., Ltd.)

E-SBR : JSR1502 / Mooney viscosity(100 deg. C)=52, Bound styrene=23.4% (JSR Corporation)

IIIR : BROMO BUTYL2244 / Mooney viscosity(125 deg. C)=46, Halogen content=2mol% (JSR Corporation)

Sulfur ¹⁾ : MUCRON OT-20 / oil con't=20wt% (Shikoku Chemicals Corporation)

Sulfur ²⁾ : GOLDEN FLOWER 200mash (Tsurumi Chemical Industry Co., Ltd.)

Peroxide : Perhexa® 25B-40 / Purity=40% (NOF Corporation)

ZnO (Sakai Chemical Industry Co., Ltd.)

Stearic acid : Lunac S-50 (Kao Corporation)

Vulcanization accelerator : DM (Ouchi Shinko Chemical Industrial Co., Ltd.)

Vulcanization accelerator : TT (Ouchi Shinko Chemical Industrial Co., Ltd.)

Silica : Ultrasil® 7000GR (Evonik Industries)

Silane coupling agent : Si69 (Evonik Industries)

Polyethylene glycol : PEG3400 (MP Biomedicals LLC)

EVA : VA con't=14%, MFR=3.4 g/10 min

Bio-LDPE: Bio-based cont.:95%, MFR=30 g/10 min

Friction coefficient measurement method that assumes the shoes

Condition

Load	2N 
Load/ Area	0.05N/cm ² (General)


Grip



The area of the hand: 140cm^2 (Men average)
Grip: 10 - 30kg (98 - 294N)
Load/ Area: $98\text{N} / 140\text{cm}^2 \times 2 = 0.35\text{N/cm}^2$
 $294\text{N} / 140\text{cm}^2 \times 2 = 1.05\text{N/cm}^2$



Relationship between load and wet grip



Compounds using SEPTON™ BIO-series SF904 (Target: Hs=60A±5)

		SEPTON™ BIO-series SF904			V-16	V-22	SBR
Hardness	Type A	21	58	57	60		
Static friction force (Wet)	Load	0.05N/cm ²	5.0	3.9	2.8		
		0.54N/cm ²	17	15	19		
		1.26N/cm ²	27	29	28		
						17	


Evaluation of SBR / SEPTON™ BIO-series combined system

Elastomer R&D department
Elastomer division

kuraray Septon™ BIO-series

Coefficient of static friction (Dry, Wet), DIN abrasion

Amount of SEPTON™ BIO-series SF904 : 5wt%, 10wt%
Improved in grip performance, less decreased DIN abrasion



Content of SEPTON™ BIO-series SF904 in polymer (wt%)	COF		DIN abrasion (Index)
	Dry	Wet	
0	100	100	100
5	112	124	107
10	117	139	96.2
15	113	133	91.6
50	108	130	43.9
100	94.2	106	38.6

*COF=Coefficient of static friction

Formulation and mechanical properties

		SB-7	SB-8	SB-9	SB-10	SB-11	SB-12
E-SBR	SBR1502	100	95	90	85	50	
SEPTON™ BIO-series	SF904		5	10	15	50	100
ZnO		3	3	3	3	3	3
Stearic acid		1	1	1	1	1	1
Silica	7000GR	35	35	35	35	35	35
Si-75		3	3	3	3	3	3
Sulfur	OT-20	2.25	2.25	2.25	2.25	2.25	2.25
Vulcanization accelerator	DM	1.1	1.1	1.1	1.1	1.1	1.1
	TT	1.1	1.1	1.1	1.1	1.1	1.1
Coefficient of static friction	Dry	5.2	5.8	6.1	5.9	5.6	4.9
	Wet	3.3	4.1	4.6	4.4	4.3	3.5
Specific gravity		1.12	1.12	1.12	1.11	1.10	1.08
Hardness	Type A	64	66	65	65	67	66
Tensile strength	MPa	14	13	12	12	7.2	21
Elongation	%	260	240	230	230	130	700
Tear strength	kN/m	62	50	51	51	37	62
DIN abrasion	mm³	73	71	79	83	173	197

Material

E-SBR : JSR1502 Mooney viscosity (100 deg. C): 52, Bound styrene: 23.4% (JSR Corporation)

SEPTON™ BIO-series: SF904

ZnO (Sakai Chemical Industry Co., Ltd.)

Steric acid: Lunac S-50 (Kao Corporation)

Silica: Ultrasil® 7000GR (Evonik Industries)

Silane coupling agent: Si75 (Evonik Industries)

Sulfur: OT-20 Total sulfur 78-82% (Shikoku Chemicals Corporation)

Vulcanization accelerator: DM (Ouchi Shinko Chemical Industrial Co., Ltd.)

Vulcanization accelerator: TT (Ouchi Shinko Chemical Industrial Co., Ltd.)

Kneading conditions

Equipment

Plastograph EC 50cc (Brabender GmbH & Co. KG)

Process

1) Kneading step 1 x 2

Rubber temp. = 150 deg. C, 5 min. x 2

⇒Polymer, ZnO, Stearic acid, Silica, Silane coupling agent etc.

a) Si75 is reactive to both silica and rubber

b) If you use Si69, you need to keep the rubber temp. below 140 deg. C.



2) Kneading step 2

Rubber temp. = < 100 deg. C (for w/o curing)

⇒Sulfur, Vulcanization accelerator



3) Sheeting (Compression molding, 160 deg. C)

Measurement condition

Friction test

ASTM D1894

Sled size: 63.5mm×63.5mm

Sled weight: 200g

Friction table material: Aluminum

Test pull rate of 150mm/min

*Wet: To measure 1.0 cc of distilled water on the table



Friction test

Hardness, Tensile strength, Elongation, Tear strength

Hardness: JIS K6253, Type A durometer

Tensile strength, Tensile Elongation: JIS K6251, Cross-head speed: 500mm/min.

Dumbbell :JIS No.3

Tear strength: JIS K6252 angle type

DIN abrasion

DIN abrasion tester (Toyo Seiki Seisaku-sho, Ltd.)

Abrasive cloth: Alumina grinding material grain size No. 60, 450×475mm

JIS K6264, Load:10N, Distance :40m

Recommended formulation for shoe soles

~ Rubber modification ~

Elastomer R&D department
Elastomer division

kuraray **Septon™** BIO-series

Recommended formulation

We recommend 7000GR as a silica and A189 as a silane coupling agent.

Step-1	E-SBR	JSR1502	90
	SEPTON™ BIO-series	SF904	10
	ZnO		3
	Stearic acid	Lunac S-50	1
	Silica	7000GR	35
	Silane coupling agent	A189	3
Step-2	Sulfur	#200	1.8
	Vulcanization accelerator	CZ	1.1
		TT	0.4
	Tc90 160 deg. C	min	4.7
	Coefficient of static friction	Dry	6.4
		Wet	3.4
	DIN abrasion	mm ³	111

Materials

Key Points [E-SBR	: JSR1502 (JSR Corporation) bound styrene 23.4%, Mooney viscosity (100 deg. C): 52
	SEPTON™ BIO-series	: SF904 (Kuraray Co., Ltd.)
	Silica	: Ultrasil® 7000GR (Evonik Industries)
	Silane coupling agent	: Silqust® A-189 (Momentive Performance Materials Inc.)
	Zinc oxide (ZnO)	: Grade No. 1 (Sakai Chemical Industry Co., Ltd.)
	Stearic acid	: Lunac S-50 (Kao Corporation)
	Sulfur	: #200
	Vulcanization accelerator-1	: Nocceler CZ (Ouchi Shinko Chemical Industrial Co., Ltd.)
	Vulcanization accelerator-2	: Nocceler TT (Ouchi Shinko Chemical Industrial Co., Ltd.)

Recommended formulation for shoe soles


~ Cross-linked EVA foam modification ~

Elastomer R&D department
Elastomer division

kuraray **Septon™** BIO-series

Recommended formulations

- Strong correlation between grip performance and hardness



		Reference	SF904	SF902
EVA (VA=19%)	EV460	100	70	90
SEPTON™ BIO-series	SF904		30	
	SF902			10
ZnO		2	2	2
Stearic acid		1	1	1
TiO ₂		4	4	4
Dicumyl peroxide	PERCUMYL D-40	0.5	0.5	0.5
Coefficient of static friction	Dry	Measured value	1.4	2.8
		Index	100	200
	Wet	Measured value	0.7	1.1
		Index	100	157
Hardness	Type A	65	54	57

Materials

EVA	: EVAFLEX® EV460 (Dow-Mitsui Polymers Co., Ltd.) VA cont. 19 wt%, MFR 2.5 g/10min. (190 deg. C, 21N)
SEPTON™ BIO-series	: SF904 and SF902 (Kuraray Co., Ltd.)
Zinc oxide (ZnO)	: Grade No. 1 (Sakai Chemical Industry Co., Ltd.)
Stearic acid	: Lunac S-50 (Kao Corporation)
Titanium(IV) oxide (TiO ₂)	: A-100 (Ishihara Sangyo Kaisha, Ltd.)
Dicumyl peroxide	: PERCUMYL® D-40, purity: 40% (NOF Corporation)

Kuraray Co., Ltd.
Elastomer Division
Tokiwabashi Tower
2-6-4, Otemachi
Chiyoda-ku, Tokyo, 100-0004, Japan

✉ elastomer@kuraray.com

→ www.kuraray.com

→ www.elastomer.kuraray.com

© KURARAY CO., LTD. 2025

SEPTON and HYBRAR are trademarks or registered trademarks of Kuraray Co., Ltd. Trademarks may not be applied for or registered in all countries.

The information provided herein corresponds to Kuraray's knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The information provided falls within the normal range of product properties and relates only to the specific material designated; this data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Final determination of suitability of any material or process and whether there is any infringement of patents is the sole responsibility of the user. Since Kuraray cannot anticipate all variations in actual end-use conditions, Kuraray makes no warranties and assumes no liability in connection with any use of this information.

kuraray Septon™ BIO-series