


Introduction of SEPTON™ HG-252 ~Hydroxyl Terminated Styrenic Thermoplastic Rubber~

Elastomer R&D Dept.
Elastomer Division

kuraray **Septon™**

Characteristics of SEPTON™ HG-252

- ✓ A primary hydroxyl group at the polymer terminal
- ✓ Reactivity and affinity to polar resins
- ✓ One-ended functional group can prevent gelation.
- ✓ Maintains good affinity to non-polar resins like polyolefins



Typical Properties of SEPTON™ HG-252

	Units	SEPTON™ HG-252	Method
Type	-	SEEPS-OH	
Styrene Content	wt%	28	
Specific Gravity	-	0.90	ISO 1183
Hardness (Type A)	-	80	ISO 7619 as reference
Tensile Strength ⁽¹⁾	MPa	25	ISO 37
Elongation ⁽¹⁾	%	500	ss reference
MFR ⁽²⁾	g/10 min	6	ISO 1133 as reference

(1) Cross-head speed: 500 mm/min at 23 deg. C

(2) 200 deg. C, 2.16 kg

Modification of Ionomer Resin using SEPTON™

Raw Materials

Ionomer Resin HIMILAN™ 1557 (DOW-MITSUI POLYCHEMICALS CO.,LTD.)
(Pre-drying: 80 deg. C for 12 hours)
HSBC SEPTON™ 2002 (Styrene content=30 wt%, SEPS)
SEPTON™ HG-252 (Styrene content=28 wt%, SEEPS-OH)

Mixing condition

Equipment	Twin screw extruder (Screw diameter 25φ, L/D=25)
Compounding temperature	200 deg. C
Screw rotation	100 rpm

Molding condition

Equipment	Injection molding machine
Temperature	Cylinder 200-220 deg. C Mold 50 deg. C

Modification of Ionomer Resin using SEPTON™

Test conditions

MFR:	ISO 1133 (230 deg. C, 2.16 kg)
Hardness:	ISO 7619
Tensile test:	ISO37 (500 mm/min, 25 deg. C)
Rebound resilience:	25 deg. C
Cut Resistance:	

V-cut method with cut resistance machine for golf ball (Dumbbell Co., Ltd) loaded 2.5 kg (height 80 cm) is used.

The cut length on the surface of test specimen is measured after cut resistance test. Shorter length means better cut resistance.

Modification of Ionomer Resin using SEPTON™

		1	2	3	
Formulations		by wt			
HIMILAN™ 1557		100	70	70	
SEPTON™ HG-252		—	30	—	
SEPTON™ 2002		—	—	30	
Properties					
MFR (230 deg. C, 2.16 kg) g/10 min		11	13	18	
Hardness (Type A)		53	43	42	
Mechanical Properties					
Tensile Modulus		MPa	200	100	110
Tensile Strength		MPa	27	28	20
Rebound resilience		%	60	60	60
Cut Resistance		mm	14	16	16

SEPTON™ HG-252 contributes to the softening of ionomer resins without the reduction of flow-ability, tensile strength, rebound resilience, and cut resistance.

Kuraray Co., Ltd.
Elastomer Division
Tokiwabashi Tower
2-6-4, Otemachi
Chiyoda-ku, Tokyo, 100-0004, Japan

✉ elastomer@kuraray.com

→ www.kuraray.com

→ www.elastomer.kuraray.com

© KURARAY CO., LTD. 2025

SEPTON is a trademark or registered trademark of Kuraray Co., Ltd. Trademarks may not be applied for or registered in all countries.

The information provided herein corresponds to Kuraray's knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The information provided falls within the normal range of product properties and relates only to the specific material designated; this data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Final determination of suitability of any material or process and whether there is any infringement of patents is the sole responsibility of the user. Since Kuraray cannot anticipate all variations in actual end-use conditions, Kuraray makes no warranties and assumes no liability in connection with any use of this information.

kuraray **Septon™**